



TORAY INDUSTRIES INC FILM DIV
FILMS BUSINESS PLANNING & ADMIN DEPT
2-1-1 NIHONBASHI MUROMACHI
CHUO-KU, Tokyo 103-8666 Japan

File Number: E86511

Lumirror: S(t)

Polyethylene Terephthalate (PET), film or sheets

(t) - Replaced by two- or three-digit alphanumeric character (beginning with 0, 1 or 2) except "104" or "15A", indicating surface treatment, deposition conditions, customer code and/or packing form.



Flammability	Value	Test Method
Flame Rating (0.038 to 0.207 mm, NC)	VTM-2	UL 94 ISO 9773
Thermal	Value	Test Method
RTI Elec		UL 746B
0.012 to 0.037 mm	105 °C	
0.038 to 0.207 mm	105 °C	
0.21 to 0.39 mm	105 °C	
RTI Elong		UL 746B
0.012 to 0.037 mm	105 °C	
0.038 to 0.207 mm	105 °C	
0.21 to 0.39 mm	105 °C	
RTI Str		UL 746B
0.012 to 0.037 mm	105 °C	
0.038 to 0.207 mm	105 °C	
0.21 to 0.39 mm	105 °C	